AMENDMENT NO. 1 DECEMBER 2021

TO

IS 1844 : 1993 BRISTLES — SPECIFICATION

(Second Revision)

(*Page* **3**, *clause* **8.1.1**) — Substitute the following for the existing:

'**8.1.1** *Burn Test*

First divide the brush into 4 segments (only for Paint brush). Take out the central tuft/segment filaments from the bottom and then perform the burn test on both sides of the filament that is, top and bottom. Each single filament of the material when burnt at the flag-end shall burn with glowing globular mass at the ignited end. Vegetable fibres burn off without this and the burning progresses rapidly towards the other end.'

(CHD 23)

Publication Unit, BIS, New Delhi, India